

## Technical Data Sheet

### ROCALEN rPE-206

Pag. 1 of 1

#### Description

Post-consumer recycled LDPE compound granules, for film extrusion.  
Available in black.

Properties	Value	Unit	Test method
<b>Physical</b>			
Density	0.97 – 1.00	g/cm <sup>3</sup>	ASTM D-792
Melt Flow Index (190°C, 2.16 kg)	0.2 – 0.8	g/10 min	ASTM D-1238
<b>Mechanical</b>			
Tensile Modulus	> 177	MPa	ASTM D-638
Tensile Stress	> 17	MPa	ASTM D-638
Tensile Strain	> 17	%	ASTM D-638
Flexural Modulus	> 158	MPa	ASTM D-790
Flexural Strength	> 9	MPa	ASTM D-790
<b>Impact</b>			
Notched Izod Impact Strength (23°C)	> 44	kJ/m <sup>2</sup>	ASTM D-256
<b>Thermal</b>			
Heat Deflection Temperature	> 46	°C	ASTM D-648

#### Note:

All information contained in this data sheet is based on typical values and intended for reference and comparison purposes only. The data above is provided in good faith but we do assume no liability for any inaccuracies or variations in actual values, nor do we assure the suitability of any material for any specific application. It is the buyer's responsibility to determine the suitability of the product for the intended application. We do not recommend our products for direct food contact applications, medical applications or toys.